

AUXQUIMIA® UNIPOL-FF™ 0.5

FLUORINE-FREE FOAM CONCENTRATE (0.5%)



DESCRIPTION

Low viscosity foam concentrate formulated with a special combination of hydrocarbon surfactants which gives excellent foaming, extinguish and burnback properties to its foam solutions. **It does not contain any organohalogenated compounds.** It can be used to put out hydrocarbons and class A (solids) fires..

USE

AUXQUIMIA® UNIPOL-FF™ 0.5 has been designed to generate foams with high fluidity and slow drainage. It is mainly used on hydrocarbon fires and could be even applied with forceful application; capacity up until now only reserved for AFFF agents. Unlike the AFFF agents, it does not form an aqueous film on hydrocarbons because it does not contain fluorinated surfac-tants. The excellent extinguish times are possible thanks to its good foaming capacity, high water retention and great oleophobicity. Due to the lack of this aqueous film, it is recommended to cover the fuel with a layer of foam thick enough to prevent that the fuel surface can be exposed and reignited. Its good wetting ability and great water retention



make it very suitable for extinguishing Class A fires (solid) with both spray and low expansion nozzles.

DOSAGE

The dilution rate is 0.5% in fresh water for hydrocarbons and class A fires. It may be proportioned with standard equipment (in-line inductors, bladder tanks, balanced pressure systems, etc).

SPECIFICATIONS

FOAM CONCENTRATE	
Specific gravity @ 20°C	1.040
pH @ 20°C	7-8
Viscosity, cone and plate, 750 s-1 mPa.s @ 20°C	12
Freezing point, °C	< -5
Lowest temperature for use, °C	-5

FOAM SOLUTIONS	
Dilution rate	0.5%
Surface tens. at 20°C, mN/m (Demineralised water)	27.0
Interfacial tens. with cyclohexane at 20°C, mN/m	<4
Low Expansion Foam (EN-1568-3)	
Foam Expansion Index	>7
25% Drainage Time, mins	>1:30

PERFORMANCE

The foam achieves a very quick knock-down of fires and shows a good burnback resistance. The product has approval certification according to EN 1568-3:2008 (Class IB) in fresh water.

STANDARD	EN-1568-3:2008	
Fuel	Heptane	
Application	Forceful	Gentle
Dilution rate, %	0.5	0.5
Water	fresh	fresh
Extinction	2:00	2:07
Burnback 25%	<10:00	16:06
Classification	IB	IB

**EN-1568
3:2008
approval**

PACKAGING

The product is supplied in 20 or 25 L PE prismatic containers, 200 L PE cylindrical drums and 1.000 L IBC containers.

STORAGE

The concentrate should be stored at temperatures between -5° and +50°C, preferably in the original containers or in stainless steel or epoxy lined tanks. Avoid permanent contact with carbon steel, iron, copper alloys, aluminium, etc. Do not mix with other foam concentrates without a previous verification of compatibility.

⚠ CAUTIONS

Foams should not be used in contact with electrical equipment, neither with chemical products that can react with water. It is recommended to avoid the contact of the foam concentrate with the skin. In case of eye splashes wash with plenty of water. In case of ingestion do not induce vomit, drink water and take medical advice.



Solutions That Save.

FOR MORE INFORMATION

Contact any of our worldwide Perimeter Solutions Fire Safety offices or visit:
www.Perimeter-Solutions.com

UNITED STATES

1520 Brookfield Avenue
Green Bay, WI 54313
Tel: +1 (920) 593-9445
salesfoamusa@perimeter-solutions.com

EMEA

Polígono Industrial de Baiña, Parcela 23
33682 Baiña-Mieres (Asturias) – Spain
Tel: +34 985 24 29 45
salesfoamea@perimeter-solutions.com

ASIA PACIFIC

3 Charles Street
St Marys NSW 2760 – Australia
Tel: +61 2 9673 5300
salesfoamapac@perimeter-solutions.com

perimeter-solutions.com

NOTICE PERIMETER SOLUTIONS MAKES NO REPRESENTATIONS OR WARRANTIES AS TO THE COMPLETENESS OR ACCURACY OF THE INFORMATION INCLUDED HEREIN. THE INFORMATION CONTAINED HEREIN IS NOT INTENDED TO PROVIDE REGULATORY, LEGAL OR EXPERT ADVICE RELATING TO THE PRODUCTS, ITS APPLICATION OR USES. NOTHING CONTAINED HEREIN IS TO BE CONSTRUED AS A RECOMMENDATION TO USE ANY PRODUCT, PROCESS, EQUIPMENT OR FORMULATION IN CONFLICT WITH ANY INDUSTRIAL PROPERTY OR INTELLECTUAL PROPERTY RIGHTS, AND PERIMETER SOLUTIONS MAKES NO REPRESENTATION OR WARRANTY, EXPRESS OR IMPLIED, THAT THE USE THEREOF WILL NOT INFRINGE ON ANY INDUSTRIAL PROPERTY OR INTELLECTUAL PROPERTY RIGHTS. NO REPRESENTATIONS OR WARRANTIES, EITHER EXPRESSED OR IMPLIED, OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE OR OF ANY OTHER NATURE ARE MADE HEREUNDER WITH RESPECT TO THE INFORMATION CONTAINED HEREIN.